

20MnCr5

Quality 16MnCr5 case hardening steel.

20MnCr5 steel suppliers, delivering round bar to the whole of the UK

This grade is a low alloy chromium, manganese case hardening steel. Carburised 20MnCr5 gives a hard case with a strong core whilst retaining a degree of toughness. It is suited for applications which require a combination of toughness and wear resistance and is commonly supplied in round bar.

[16MnCr5](#) is also available in a limited range of diameters, please contact our sales team for further details.

We welcome export enquiries for [case hardening steel](#). Contact our sales office and consult our shipping policy for further details.

Alternative case hardening grades we supply

| [EN32](#) | [EN36](#) | [16MnCr5](#)

Form of Supply

West Yorkshire Steel are suppliers of 20MnCr5 round bar. Diameters in in grade 20MnCr5 can be sawn to your required lengths as one offs or multiple cut pieces. Centreless ground steel bar can be supplied, providing a case hardening steel precision ground bar to close tolerances.

Applications

This carburising steel grade is commonly used in the engineering and automotive industries for a wide variety of components such as shafts, gears, collets, pins, camshafts and pinions.



Contact our experienced sales team who will assist you with your enquiry.

- Diameter

Analysis

Carbon	0.17-0.22%	Silicon	0.40% max
Manganese	1.00-1.40%	Chromium	1.00-1.30%
Phosphorous	0.025% max	Sulphur	0.035% max

Carburising / Case Hardening

Case hardening will give a hard wear resisting surface combined with a tough core strength. Case hardening temperatures range from 780-820°C, followed by rapid quenching and tempering which will determine the resulting hardness

Heat Treatment

When hardening 20MnCr5 heat treatment temperatures, including rate of heating, cooling and soaking times will vary due to factors such as the shape and size of each steel component. Other considerations during heat treatment include the type of furnace, quenching medium and work piece transfer facilities. Please consult a heat treatment specialist for full guidance on heat treatment of 20MnCr5 steel

Certification

20MnCr5 case hardening steel is available with a cast and analysis certificate or BS EN 10204 3.1 mill certificate, please request when placing any orders.

Quality Assured Supply

20MnCr5 is supplied in accordance with our ISO 9001:2015 registration.



**West Yorkshire Steel
Ltd**
Sandbeck Industrial Estate,
Wetherby, Leeds,

Call: 01937 584440

Fax: 01937 580128

Email:

  [westyorkssteel.com](http://www.westyorkssteel.com)

QUOTE ME



Information provided on our datasheets has been drawn from various recognised sources, including British, European and International Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources. Material supplied by the Company may vary significantly from this data but will conform to all relevant and applicable standards. Any of the products detailed may be used for a large range of purposes and as WYS has no control over their use; WYS specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied. © West Yorkshire Steel Ltd. All Rights Reserved.