Applied Rubber Linings Ltd

Process Plant Liners

Technical Data Sheet



Material Reference : ARL/68 AS

Antistatic and Abrasion Resistant Soft Natural

Rubber.

Description & Application: FOR SPECIFIC APPLICATIONS

PLEASE CONTACT APPLIED RUBBER LININGS LIMITED.

ARL/68 AS is a highly abrasive resistant soft natural rubber plant lining material, specifically formulated to be antistatic and with good resistance to many acids and chemicals.

Temperature Range : -35°C to 80°C (Depending upon conditions

and applications).

Specific Gravity : 1. 15

Hardness : $65^{\circ} \pm 5^{\circ}$ SHORE 'A'

Tensile Strength : 19.2 MPa

Elongation At Break : 315%

Compression Set : 17.8%

Electrical Resistivity : N/A.

Health & Safety : See COSSH assessments

Typical Applications : Particularly useful for lining shot blasting equipment

(reclaimers etc) where the build up of static can damage

Tel: 01452 381849

the rubber lining.

NOTE:- INFORMATION GIVEN IN GOOD FAITH BUT DETAILS MAY

CHANGE WITHOUT PRIOR NOTIFICATION. CUSTOMERS

SHOULD MAKE THEIR OWN ASSESSMENTS TO DETERMINE THAT THE MATERIALS ARE SUITABLE FOR SPECIFIC APPLICATIONS