



AISI 4340 Alloy Steel

Quality 4340 alloy steel cut and delivered straight to your workshop.

AISI 4340 alloy steel stockholders and suppliers, delivering to the whole of the UK.

AISI 4340 is a nickel chromium molybdenum alloy steel specification widely used in the oil and gas sectors. As a quality grade alloy steel, it offers toughness and high strength in the heat treated condition, with good fatigue strength. Available in round bar 4340 is available fully certified and suitable for applications requiring a quality high tensile alloy steel. AISI 4340 is commonly supplied quenched and tempered with a hardness of between 24 to 29HRc.

Other AISI [oil and gas steel](#) grades we supply:

[4130](#) | [4140](#) | [4145](#) | [4330](#) | [8620](#) | [6150](#) |

Form of Supply

West Yorkshire Steel are AISI 4340 steel stockholders and suppliers of round bar. Diameters can be supplied as full bar lengths or cut blanks. AISI 4340 ground steel bar can be supplied, providing a high tensile alloy steel precision ground bar to tight tolerances.



Contact our experienced sales team who will assist you with your AISI 4340 enquiry.

■ Diameter

Applications

4340 steel is suited for shock loading or stress concentration applications such as shafts, gears, bolts, nuts, pins and couplings.

Analysis

Carbon	0.38-0.43%	Silicon	0.15-0.35%
Manganese	0.60-0.80%	Chromium	0.70-0.90%
Molybdenum	0.20-0.30%	Nickel	1.65-2.00%
Sulphur	0.025% max.	Phosphorous	0.025% max.

Forging

Preheat the steel carefully, then raise the temperature to 1150-1210°C for forging. Do not forge below 850°C. It has good forging characteristics but care must be taken when cooling as the steel shows susceptibility to cracking. Cooling in ash or lime after forging is recommended.

Annealing

Heat the steel slowly to 800-860°C and allow enough time for the steel to be thoroughly heated. Cool slowly in the furnace.

Stress Relieving

When components are heavily machined, ground or otherwise subject to cold work, stress relieving will be beneficial prior to hardening.

Hardening

4340 steel is usually supplied ready heat treated. If further heat treatment is required annealed 4340 should be heated slowly to 830-865°C and after adequate soaking at this temperature quench in oil. Temper as soon as the steel reaches room temperature.

Tempering

Heat the steel carefully to a suitable temperature selected by reference to a tempering chart or table, soak at the temperature for 2 hours per 25mm of section, then allow to cool in air.

Heat Treatment

Heat treatment temperatures, including rate of heating, cooling and soaking times will vary due to factors such as the shape and size of each 4340 steel component. Other considerations during the heat treatment process include the type of furnace, quenching medium and work piece transfer facilities. Please consult your heat treatment provider for full guidance on heat treatment of AISI 4340 steel.

Quality Assured Supply

4340 alloy steel is supplied in accordance with our ISO 9001:2015 registration.



West Yorkshire Steel Ltd
Sandbeck Industrial Estate,
Wetherby, Leeds,
LS22 7DN UK

Call: 01937 584440
Fax: 01937 580128
Email: sales@westyorkssteel.com
 

QUOTE ME



Information provided on our datasheets has been drawn from various recognised sources, including British, European and International Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources. Material supplied by the Company may vary significantly from this data but will conform to all relevant and applicable standards. Any of the products detailed may be used for a large range of purposes and as WYS has no control over their use; WYS specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied. © West Yorkshire Steel Ltd. All Rights Reserved.